

Diversified Silicone Products, Inc.

13937 Rosecrans Ave.

Santa Fe Springs, CA 90670

Tel: (562) 404-8942 Fax: (562) 404-1323

Other Data Sheets Are Available On Our Website

www.diversifiedsilicone.com



SILICONE SHEETING

FLUOROSILICONE SHEETING

“DSP70FS”

70 Shore “A”

DESCRIPTION:

Fluorosilicone sheeting is designed to be used in applications where normal silicone would degrade by harsh chemicals or fluids and is used where extreme conditions exist. This material will perform within a temperature range of -65 F to +500 F. Fluorosilicone is extremely resistant to fuels and solvents, and naturally resistant to ozone. It is available in various thickness and widths. Contact customer service for the size that best fits your needs.

FEATURES:

- Excellent Gasketing Material
- Resistant to Harsh Chemicals, Fuels, Solvents
- Extreme High & Low Temperature Resistant
- Low Compression Set
- Fungus Resistant
- UV / Ozone Resistant

SPECIFICATIONS:

MIL-R-25988 TY2 CL1 GR70

PHYSICAL PROPERTIES

PROPERTIES	Test Method	Typical Properties
Specific Gravity, G/CC	ASTM D297	1.50
Durometer, Shore “A”	ASTM D2240	70
Tensile Strength, PSI	ASTM D412	950
Elongation, %	ASTM D412	175
Tear, PPI DIE “B”	ASTM D624	80
Temperature Range	(°F)	-65 to +450 (+500 Intermittent)
Volume Change %		
Fuel “C” 22 hrs @ 77 F		20%

The above values are typical properties and are provided for information only. They should not be used to set specification requirements. It is up to the end user to determine whether the material is suitable for the intended application.